

生コン工場 規 格		W/C	1	2	3	4	5	6	7	8	9	10	11	12
			更水生コン(株)	信州生コン(株) 更埴工場	信州生コン(株) 豊野工場	信州生コン(株) 大橋工場	(株)宮下 宮下生コン工場	さくら生コン(株) 須坂工場	西山生コン(株)	(株)ホリウチ 堀内生コン工場	長野生コン(株)	宮島産業(株) 宮島生コン工場	(株)本久 長野生コン工場	(有)轟商会
1	18-8-25-BB	60% 以下 65% 以下	●		●		●		●	●	●	●	●	●
2	18-8-40-BB	60% 以下 65% 以下	●		●		●		●	●	●	●	●	●
3	21-5-40-BB	55% 以下 60% 以下	●		●				●			●	●	
4	21-8-25-BB	55% 以下 60% 以下 65% 以下	●	●	●	●	●	●	●	●	●	●	●	●
5	21-8-40-BB	55% 以下 60% 以下 65% 以下	●	●	●	●	●	●	●	●	●	●	●	●
6	21-12-40-BB	55% 以下									●			
7	24-5-40-BB	60% 以下 55% 以下	●						●					
8	24-8-25-BB	50% 以下 55% 以下 60% 以下	●	●	●	●	●	●	●	●	●	●	●	●
9	24-8-40-BB	50% 以下 55% 以下 60% 以下	●	●	●	●	●	●	●	●	●		●	●
10	24-12-25-BB	50% 以下 55% 以下		●	●	●	●	●			●		●	
11	24-12-40-BB	50% 以下 55% 以下		●	●	●	●	●			●		●	
12	30-8-25-BB	45% 以下 50% 以下 55% 以下			●									●
13	30-12-25-BB	55% 以下 45% 以下	●						●	●			●	
14	曲-4.5-2.5-40-BB	45% 以下 315 kg以上										●		
15	曲-4.5-6.5-40-BB	45% 以下 315 kg以上										●		
16	18-8-25-N	65% 以下	●		●					●		●		●
17	18-8-40-N	65% 以下	●		●					●		●		●
18	21-5-40-N	60% 以下	●									●		
19	21-8-25-N	60% 以下 65% 以下	●		●				●	●		●		●
20	21-8-40-N	60% 以下 65% 以下	●		●				●	●		●		●
21	24-5-40-N	60% 以下	●											
22	24-8-25-N	50% 以下 55% 以下 60% 以下	●		●				●	●	●	●		●
23	24-8-40-N	50% 以下 55% 以下 60% 以下	●		●				●	●				●
24	24-12-25-N	55% 以下			●						●			
25	24-12-40-N	55% 以下			●									
26	30-8-25-N	50% 以下 55% 以下	●		●				●	●	●			●
27	30-12-25-N	50% 以下 55% 以下			●						●			
28	曲-4.5-2.5-40-N	45% 以下 315 kg以上												
29	曲-4.5-6.5-40-N	45% 以下 315 kg以上										●		
30	18-8-25-H	60% 以下 65% 以下	●		●		●		●	●		●	●	●
31	18-8-40-H	60% 以下 65% 以下	●		●		●		●	●			●	●
32	21-8-25-H	55% 以下 60% 以下 65% 以下	●		●		●		●	●		●	●	●
33	21-8-40-H	55% 以下 60% 以下 65% 以下	●		●		●		●	●		●	●	●
34	24-8-25-H	55% 以下 60% 以下	●		●		●		●	●			●	●
35	24-8-40-H	50% 以下 55% 以下	●		●		●		●	●		●	●	●
36	24-12-25-H	55% 以下			●		●						●	
37	24-12-40-H	55% 以下			●		●						●	
38	27-8-25-H	50% 以下										●		
39	30-8-25-H	50% 以下 55% 以下	●						●		●			●
40	30-12-25-H	55% 以下									●			
41	36-8-25-H	55% 以下									●			
42	36-12-25-H	55% 以下									●			
43	40-8-25-H	55% 以下									●			
44	40-12-25-H	55% 以下									●			

(注1) 設計単価との整合を図る際には、水セメント比を指定して下さい。

(注2) 「捨てコン」はJIS規格外製品であり、判定基準がないので一括承認の対象としません。